

Technical specification

SILPAULIN
The Toughest Tarpaulin
AS PER IS 14611 - 1988

TECHNICAL VALUES OF MULTILAYERED CROSS LAMINATED XF FILM (AS PER IS:14611:1998 STANDARD)								
SR.No	Test Specification	UNITS	GSM					
			70	90	120	150	200	250
1	Tensile Strength at break MD IS-14611-1998 CD IS-14611-1998	kg/cm ²	386	375	337	337	295	270
			435	412	365	360	312	283
2	Elongation at break MD IS-14611-1998 CD IS-14611-1998	%	400	400	400	400	400	400
			300	300	300	300	300	300
3	Dart Impact Strength IS-14611-1998	GSM	250	325	400	700	800	900
4	Elmendorf Tearing Test MD IS-14611-1998 CD IS-14611-1998	GSM	1200	1500	2080	2880	3500	4000
			900	1200	1600	2400	3000	3500

THE ABOVE VALUES MAY VARY AS PER ACTUAL GSM OF THE SAMPLE
THE ABOVE VALUES ARE FOR SINGLE COLOUR FILM
IS-14611-1998 MARKED PRODUCTS AVAILABLE ON REQUEST

Note: Subject to change without notice, all information given in good faith without any guarantee of any nature.


Authorised Dealer -



SILPAULIN
The Toughest Tarpaulin
AS PER IS 14611 - 1988

Applications :

A **Supreme** Product
"XF Division"



FUMIGATION




CONSTRUCTION



POND LINING



AGRICULTURE



CHILLI DRYING



TRANSPORT